

Dipl.-Ing. Stefan Pauly
Dipl.-Phys. Annette Becker
Fachlaboratorium für Permeationsprüfung
Zeilstraße 30, D-65201 Wiesbaden
Tel: +49/611/260216 Fax: +49/611/260213

order number: DIG07003

Customer: Dinamik Isi lLtd. Şti.
1203/4 Sk. No.1/A Ege Ticaret Merkezi
Yenişehir – İZMİR

Product tested	Thickness			Relative humidity	Temperatur	Water vapor transmission rate	Water vapor transmission rate	Density	Water vapor resistance factor μ	Equivalent airlayer thickness
	min	max	MW							
	mm	mm	mm	%	°C	g/(m*d)	g/(m ² *d)	kg/m ³	--	m
Dynaflex 19 mm	17,5	19,5	18,7	50	23	—	0,40	30	3230	60

Date: 17. July 2007

measured by:

Becker

Dipl.-Ing. Stefan Pauly
Dipl.-Phys. Annette Becker
Fachlaboratorium für Permeationsprüfung
Zeilstraße 30, D-65201 Wiesbaden
Tel: +49/611/260216 Fax: +49/611/260213

order number: DIG07001

Customer: Dinamik Isi lLtd. Şti.
1203/4 Sk. No.1/A Ege Ticaret Merkezi
Yenişehir – İZMİR

Product tested	Thickness			Relative humidity	Temperatur	Water vapor transmission rate	Water vapor transmission rate	Density	Water vapor resistance factor μ	Equivalent airlayer thickness
	min	max	MW							
	mm	mm	mm	%	°C	g/(m*d)	g/(m ² *d)	kg/m ³	--	m
Dynaflex 19 x 28*	19,9	21,4	20,5	50	23	0,052	0,35	32	3290	67

Date: 17. July 2007

measured by:

Becker

* The calculation is based on the measured inner diameter of 29 mm.

Dipl.-Ing. Stefan Pauly
Dipl.-Phys. Annette Becker
Fachlaboratorium für Permeationsprüfung
Zeilstraße 30, D-65201 Wiesbaden
Tel: +49/611/260216 Fax: +49/611/260213

order number: DIG07001

Determination of the thermal conductivity

Customer: Dinamik Isi ILtd. Şti.
1203/4 Sk. No.1/A Ege Ticaret Merkezi
Yenişehir – İZMİR

Product name: Dynaflex • 19 x 28

Diameter of the test tube: 28,0 mm
Thickness: 20,5 mm
Density: 32 kg/m³

Sample conditioning: The sample has been tested like delivered.

mean temperature °C	thermal conductivity λ W/(m·K)
9,02	0,03946
19,31	0,04171
28,95	0,04379
38,71	0,04629

mean temperature °C	0	10	20	30	40
thermal conductivity W/(m·K)	0,037	0,040	0,042	0,044	0,046

Date: 17. July 2007

tested by:

Becke

Thermal conductivity of Dynaflex, 19 x 28.

